

МАТЕРИАЛ: 1.2344

ТВЁРДОСТЬ СТЕРЖНЯ:

Поверхность: 70 HRC

Сердцевина: 40-45 HRC


ТВЁРДОСТЬ ГОЛОВКИ: 45+/-5 HRC

ЖЕСТКОСТЬ СЕРДЦЕВИНЫ: 150 Kp/mm2

НОРМАТИВ: DIN 1530-ISO 8693. Толкатель плоский оксидированный, идеально подходит для извлечения в зоне рёбер/краев отливаемой детали.

РАБОЧАЯ ТЕМПЕРАТУРА: до 650°C

ПРИМЕР ЗАКАЗА: LAN-A*B*L



L1						30	40	50	65	80	100	125	155
L						60	80	100	125	160	200	250	315
A (-0,015)	B (-0,015)	d g6	D (-0,2)	K (-0,05)	r								
0,8	3,5	4,0	8,0	3,0	0,3	•	•	•	•				
1,0	3,5	4,0	8,0	3,0	0,3	•	•	•	•				
1,2	3,5	4,0	8,0	3,0	0,3	•	•	•	•				
0,8	3,8	4,2	8,0	3,0	0,3	•	•	•	•				
1,0	3,8	4,2	8,0	3,0	0,3	•	•	•	•	•			
1,2	3,8	4,2	8,0	3,0	0,3	•	•	•	•	•	•		
1,0	4,5	5,0	10,0	3,0	0,3		•	•	•	•	•		
1,2	4,5	5,0	10,0	3,0	0,3		•	•	•	•	•		
1,5	4,5	5,0	10,0	3,0	0,3		•	•	•	•	•		
1,6	4,5	5,0	10,0	3,0	0,3		•	•	•	•	•		
1,8	4,5	5,0	10,0	3,0	0,5		•	•	•	•	•		
1,0	5,5	6,0	12,0	5,0	0,5		•	•	•	•	•		
1,2	5,5	6,0	12,0	5,0	0,5			•	•	•	•		
1,5	5,5	6,0	12,0	5,0	0,5			•	•	•	•		
1,6	5,5	6,0	12,0	5,0	0,5			•	•	•	•		
1,8	5,5	6,0	12,0	5,0	0,5				•	•	•		
2,0	5,5	6,0	12,0	5,0	0,5				•	•	•		
1,5	7,5	8,0	14,0	5,0	0,5				•	•	•		

МАТЕРИАЛ: 1.2344

ТВЁРДОСТЬ СТЕРЖНЯ:

Поверхность: 70 HRC

Сердцевина: 40-45 HRC


ТВЁРДОСТЬ ГОЛОВКИ: 45+/-5 HRC

ЖЕСТКОСТЬ СЕРДЦЕВИНЫ: 150 Kp/mm2

НОРМАТИВ: DIN 1530-ISO 8693. Толкатель плоский оксидированный, идеально подходит для извлечения в зоне рёбер/краев отливаемой детали.

РАБОЧАЯ ТЕМПЕРАТУРА: до 650°C

ПРИМЕР ЗАКАЗА: LAN-A*B*L



L1						30	40	50	65	80	100	125	155
L						60	80	100	125	160	200	250	315
A (-0,015)	B (-0,015)	d g6	D (-0,2)	K (-0,05)	r								
1,6	7,5	8,0	14,0	5,0	0,5				•	•	•		
1,8	7,5	8,0	14,0	5,0	0,5				•		•		
2,0	7,5	8,0	14,0	5,0	0,5				•		•		•
1,8	9,5	10,0	16,0	5,0	0,8						•	•	
2,0	9,5	10,0	16,0	5,0	0,8						•	•	•
1,5	10,0	12,0	18,0	7,0	0,8				•		•	•	
1,8	10,0	12,0	18,0	7,0	0,8						•	•	
2,0	10,0	12,0	18,0	7,0	0,8						•	•	
2,0	11,5	12,0	18,0	7,0	0,8				•		•		•
1,8	12,0	14,0	22,0	7,0	0,8						•	•	
2,0	12,0	14,0	22,0	7,0	0,8						•	•	
2,0	15,0	16,0	22,0	7,0	0,8						•	•	•
2,5	15,0	16,0	22,0	7,0	0,8							•	•
3,0	19,0	20,0	26,0	8,0	1,0						•	•	•
4,0	19,0	20,0	26,0	8,0	1,0							•	•